

19



Europäisches Patentamt

European Patent Office

Office européen des brevets

11 Veröffentlichungsnummer:

11 Publication number:

11 Numéro de publication:

0 674 720

Internationale Anmeldung veröffentlicht durch die
Weltorganisation für geistiges Eigentum unter der Nummer:

WO 94/13842 (art.158 des EPf).

International application published by the World
Intellectual Property Organisation under number:

WO 94/13842 (art.158 of the EPC).

Demande internationale publiée par l'Organisation
Mondiale de la Propriété sous le numéro:

WO 94/13842 (art.158 de la CBE).

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C21D 7/10, C22C 38/00	A1	(11) International Publication Number: WO 94/13842 (43) International Publication Date: 23 June 1994 (23.06.94)
(21) International Application Number: PCT/US93/12043 (22) International Filing Date: 10 December 1993 (10.12.93) (30) Priority Data: 07/992,123 17 December 1992 (17.12.92) US (71) Applicant: CONSOLIDATED METAL PRODUCTS, INC. [US/US]; 1028 Depot Street, Cincinnati, OH 45204 (US). (72) Inventor: GALLAGHER, Hugh, M., Jr.; 7262 State Road, Cincinnati, OH 45230 (US). (74) Agents: JOSEPHIC, David, J. et al.; Wood, Herron & Evans, 2700 Carew Tower, Cincinnati, OH 45202 (US).		(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, LV, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: COLD FORMED HIGH-STRENGTH STEEL PARTS (57) Abstract A method of making high-strength steel parts is disclosed by providing a blank of high-strength steel having a ferrite-pearlite microstructure and high-strength mechanical properties and cold forming the blank by upsetting, forging, or extrusion to provide a part having a desired geometric configuration while the mechanical strength of the part remains substantially the same or greater than the blank.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

-1-

COLD FORMED HIGH-STRENGTH STEEL PARTS**RELATED APPLICATION**

This application is a continuation-in-part application of United States patent application serial No. 07/848,646, filed March 9, 1992, which is, in turn, a continuation-in-part application of United States patent
5 application serial No. 07/602,675, filed October 24, 1990 and now U.S. Patent No. 5,094,698, both assigned to the assignee of this application.

FIELD OF THE INVENTION

The present invention relates to a method of making high-strength steel parts, and more particularly, it relates to a method in which a blank of high-
10 strength steel is cold formed into a part having a desired geometric configuration, such that the strength of the part remains substantially the same or greater than the blank.

BACKGROUND OF THE INVENTION

A number of methods have heretofore been used to make steel
15 parts. These methods often employ cold forming techniques, such as upsetting, heading and extrusion, which are well known in the art. In upsetting, the cross-sectional area of a portion or all of a blank of metal is increased. Heading is a particular form of upsetting where the blank is a wire, rod or bar stock. The

-2-

heads of bolts are often made using heading techniques. In extrusion, the metal blank is forced through a die orifice of desired cross-sectional outline to produce a length of uniform cross section.

One such method for making high-strength steel parts which is well known begins by annealing or otherwise softening the steel blank. The annealed steel blank is then cold formed, in a process which includes one of the above type forming techniques, into a desired geometric configuration. The now formed part is then heat treated, i.e., austenitized, hardened by quenching and tempered, to obtain the high-strength mechanical properties desired. The steel material of the resulting part has a tempered martensite microstructure. The mechanical properties produced from such heat treatments are often inconsistent and can vary widely from part to part. In addition, the annealing and heat treating steps significantly add to the cost of the overall process for making the high-strength steel parts, due in large part to the energy consumption associated with heating the part.

In another method for making such high-strength steel parts, the blank of steel is initially austenitized, hardened by quenching and then tempered to the point where the mechanical properties of the post-heat treated blank are such that the blank can be subsequently cold formed, in a process which includes one of the above three forming techniques, into a desired geometric configuration. The steel material of the finished part from this method also has a tempered martensite microstructure. While this method apparently has advantages over the previously described method in that narrower strength tolerances from part to part

-3-

have reportedly been obtained, this method still employs a costly heat treating process.

Cold forming blanks of high-strength material is known. In U.S. Patent No. 3,904,445 issued to the present inventor, a method is disclosed for cold forming a length of high-strength steel bar stock into a U-bolt. The '445 patent discloses such a length of bar stock made of a steel material having a composition consisting essentially of, by weight percent: carbon between about 0.50- 0.55%, manganese between about 1.20-1.65%, vanadium between about 0.03-0.05%, with the balance substantially all iron. However, cold forming a bend in a length of bar stock is less severe than other cold forming techniques, such as upsetting and extruding. Until this invention, it was thought that cold forming a blank of high-strength into a part by upsetting or extrusion type techniques would likely result in the formation of cracks or even fractures in the finished high-strength steel part or at the least would likely require the gradual formation of the part by a series of cold forming steps with an annealing or stress relieving step performed between successive cold forming operations. Such cracks or fractures would likely ruin the part. In addition, employing such cold forming and annealing steps would add to the time and cost of making such high strength steel parts.

20 SUMMARY OF THE INVENTION

There has heretofore been lacking a method of making a high-strength steel part from a blank of steel having a ferrite-pearlite microstructure and possessing desired high-strength properties, which method includes a cold-forming step whereby the blank is cold formed by upsetting, forging, or extrusion

-4-

type techniques into a desired part, with the mechanical strength of the part remaining substantially the same or greater than the strength originally possessed by the blank, and with the part produced with the desired high-strength mechanical properties without the need of heat treatment. The term "blank" as used herein
5 has its usual meaning, i.e., a piece of metal to be cold formed into a finished part of desired geometric configuration. Blanks include such pieces of metal as bar stock (i.e., a piece of steel long in proportion to its width or thickness).

The present invention is directed to a method of making high-strength steel parts from blanks of high-strength steel material having a ferrite-
10 pearlite microstructure and a tensile strength of at least about 120,000 psi and a yield strength of at least about 90,000 psi with the following composition by weight percent: carbon - about 0.30 to about 0.65 %, manganese - about 0.30 to about 2.5 %, at least 1 grain refiner from the group consisting of aluminum, niobium (i.e., columbium), titanium and vanadium and mixtures thereof, in an
15 amount effective up to about 0.35 %, and iron - balance.

In one of its aspects, the present invention provides a method of making high-strength steel parts from such blanks by cold forming the blank using techniques such as upsetting, forging, or extrusion to provide a part having the desired geometric configuration with a ferrite-pearlite microstructure, whereby the
20 mechanical properties of tensile strength and yield strength of the part are substantially the same or greater than the blank.

The present invention also provides a method of making high-strength steel parts which includes cold forming a blank of high-strength steel using such techniques, whereby the mechanical properties of tensile strength and

-5-

yield strength are substantially the same or greater than the blank and wherein the part, with the desired mechanical properties of tensile strength and yield strength, is produced without the need for further processing steps to improve toughness.

Depending at least in part on its geometric configuration, some parts may need to
5 be stress relieved within a temperature range of between about 450°F to about 1,200°F in order to raise, lower, or otherwise modify the physical characteristics of the steel part (e.g., tensile strength, yield strength, percent elongation, hardness, percent reduction of area, etc.).

The principles of this invention, its objectives and advantages will
10 be further understood with reference to the following detailed description.

DETAILED DESCRIPTION OF THE INVENTION

The method of the present invention is useful for producing a wide variety of finished high-strength steel parts including various types of bolts (U-bolts, eye-bolts, J-bolts, hex-head bolts, square-head bolts, etc.), axles, camshafts,
15 screws, swaybars and other parts susceptible to forming by the cold forming process described herein.

In a preferred embodiment, the method of the present invention for making a high-strength steel part includes providing a blank of high-strength steel material having a microstructure of fine pearlite in a ferritic matrix, a tensile
20 strength of at least about 120,000 psi and preferably at least about 150,000 psi, and a yield strength of at least about 90,000 psi, and preferably at least about 130,000 psi. Pearlitic constituents are generally considered to be "fine" when their lamellae are not resolvable at an optical magnification of about 1000 times. In one form, the high-strength steel material utilized as the blank has been hot

-6-

reduced and cold drawn to provide the blank having the mechanical properties of tensile strength and yield strength stated above.

The high-strength steel material used to make the blank has the following composition, by weight percent:

- 5 carbon about 0.30 to about 0.65 %
 manganese about 0.30 to about 2.5 %
 at least 1 ferrous grain refiner from the group consisting of
 aluminum, niobium, titanium and vanadium, and mixtures thereof,
 in an effective amount up to about 0.35 %
10 iron balance.

In a more preferred form, the high-strength steel material has the following composition, by weight percent:

- carbon about 0.50 to about 0.55 %
 manganese about 1.20 to about 1.65 %
15 at least 1 ferrous grain refiner from the group consisting of
 aluminum, niobium, titanium and vanadium, and mixtures thereof,
 in an effective amount from about 0.03 to about 0.15 %
 iron balance.

20 While aluminum, niobium (i.e., columbium), titanium and vanadium act as grain refiners, vanadium is the most preferred of the grain refiners.

The blank, having a composition and mechanical properties of tensile strength and yield strength as given above is thereafter cold formed using such techniques as upsetting, forging, or extrusion at a temperature between ambient or room temperature up to less than about 300°F, and preferably at about

-7-

ambient temperature, to provide a part having a desired geometric configuration, whereby the mechanical properties of tensile strength and yield strength of the part are substantially the same or greater than the blank. The formed part, with the mechanical properties of tensile strength and yield strength given, is preferably
5 produced without the need for further processing steps, such as a final stress relieving step, to improve toughness. However, for certain geometric configurations and applications of the part, a stress relieving step may be necessary.

The blank of high-strength steel material having a tensile strength of
10 at least about 120,000 psi and a yield strength of at least 90,000, which is used as the starting piece in the method of the present invention, is produced by any suitable method known in the art. One such method is disclosed in U.S. Patent No. 3,904,445 to the present inventor and the specification in its entirety is incorporated herein by reference. The '445 patent discloses a processing sequence
15 to produce a high-strength steel bar stock of the type particularly useful for producing threaded fasteners, including U-bolts. In the described process, the bar stock produced has a fine grained structure between about ASTM No. 5-8. In the disclosed process, a steel, having a chemistry falling within certain disclosed ranges, is subjected to a standard hot reducing operation to within 10%-15% of
20 final gauge. The hot reduced bar stock is then cut or severed into individual lengths for rapid air cooling. Thereafter, the individual lengths of hot reduced bar stock are subjected to a cold finishing to final gauge. The final step is a controlled stress relieving step to increase the mechanical strength properties. This stress relieving step comprises heating the lengths of bar stock to between

-8-

about 500-850°F for about one hour, but may or may not be necessary. Thus, such bar stock, with and without further stress relieving may be used to form the starting high-strength steel blank.

The following example illustrates the practice of the present invention to produce a hex-head bolt from high-strength steel bar stock produced in accordance with the method disclosed in my U.S. Patent No. 3,904,445 described above.

EXAMPLE

High-strength steel bar stock of equivalent to grade 8 strength steel, having a diameter of $\frac{1}{2}$ " is cut to lengths of approximately 4". This stock has a tensile strength of at least about 150,000 psi and a yield strength of at least 130,000 psi, with a ferrite-fine pearlite microstructure and a fine grain structure. One end of each bar stock segment is threaded using known threading processes, such as rolling, to provide $1\frac{1}{2}$ " inches of thread thereon. With the bar stock segment at about room temperature, the hex-head of the bolt is formed by heading, one or more times, the other end of each bar stock segment with a hex-shaped die using a mechanical forging press applying approximately 150 tons of pressure. The hex-head of the resulting bolt is approximately $\frac{3}{8}$ " thick and $\frac{3}{4}$ " wide. The mechanical properties of tensile strength and yield strength of the finished hex-head bolt product are substantially the same or greater than that originally possessed by the bar stock, and therefore, no further strengthening processing steps are required. The finished hex-head bolt product also has enough of the desired mechanical property of ductility originally possessed by the bar stock that the need for further processing steps to improve toughness can generally

be eliminated. However, for certain uses of the hex-head bolt, a stress relieving step may be necessary. For example, in some applications it is not desirable for a bolt to break under its head when pulled in tension. It is usually more desirable for the threads to be the weakest point of the bolt. In such instances, stress relieving improves the toughness of the bolt such that it breaks in its threads under tensile loading.

Compared to prior methods which used a heat treating process (i.e., austenitizing, hardening by quenching and tempering), especially when the heat treatment was used after cold forming to produce the desired high-strength mechanical properties of the part, finished parts made according to the present invention are more likely to consistently have mechanical properties which fall within a narrower range. This position is supported by the results of mechanical strength tests performed on sample hex-head bolts produced by a method according to the present invention and sample hex-head bolts produced by a prior art method which included a heat treating process performed after cold forming. For example, a total of 50 Grade 8, $\frac{1}{2}$ " x $3\frac{1}{2}$ " heat treated hex-head bolts had tensile strengths ranging from as low as 150,000 psi to as high as 172,000 psi; the mean being 160,000 psi. On the other hand, 50 Grade 8, $\frac{1}{2}$ " x $3\frac{1}{2}$ " hex-head bolts made according to the present invention exhibited tensile strengths ranging from a low of only 166,000 psi and a high of 170,000 psi, with a mean of 168,000 psi. Thus, the present invention is more likely to consistently produce higher strength steel parts within a narrower range.

The scope of the present invention is not intended to be limited by the examples provided herein, but rather as defined by the appended claims.

-10-

What is claimed is:

1. A method of making a high-strength steel part comprising the steps
o f:

providing a blank of high-strength steel material having a ferrite-
pearlite microstructure and a tensile strength of at least about 120,000 psi and a
5 yield strength of at least about 90,000 psi that comprises by weight:

carbon about 0.30 to about 0.65%

manganese about 0.30 to about 2.5%

at least one element from the group consisting of aluminum,
niobium, titanium and vanadium, and mixtures thereof, in an
10 effective amount for grain refining up to about 0.35%

iron balance; and

cold forming said blank by upsetting, forging or extrusion to
provide a part having a desired geometric configuration, whereby the mechanical
properties of tensile strength and yield strength of said part are substantially the
15 same or greater than said blank.

2. The method of claim 1 wherein said part with said mechanical
properties are produced without the need for further processing steps to improve
toughness.

20

3. The method of claim 1 wherein the high-strength steel material has
previously been hot reduced and cold drawn to provide said blank.

-12-

4. The method of claim 1 wherein the blank of high-strength steel material has a tensile strength of at least about 150,000 psi and a yield strength of at least about 130,000 psi.
- 5 5. The method of claim 1 wherein the high-strength steel material comprises, by weight percent:
- carbon about 0.50 to about 0.55%
- manganese about 1.20 to about 1.65%
- at least one grain refiner from the group consisting of aluminum,
- 10 niobium, titanium and vanadium, and mixtures thereof, in an
- amount from about 0.03 to about 0.15%
- iron balance.
- 15 6. The method of claim 1 wherein said cold forming is carried out at ambient temperature up to less than about 300°F.
7. The method of claim 1 wherein said blank of high-strength steel material has a microstructure of fine pearlite in a ferritic matrix.
- 20 8. The method of claim 1 wherein said part with said mechanical properties is subjected to stress relieving within a temperature range between about 450°F to about 1,200°F in order to modify the physical characteristics of said part.

9. A method of making a high-strength steel part comprising the steps of:

providing a blank of high-strength steel material having a ferrite pearlite microstructure, a tensile strength of at least about 120,000 psi and a yield strength of at least about 90,000 psi, which material has previously been hot reduced and cold drawn to provide said blank with said high-strength properties, said high-strength steel comprising, by weight percent:

carbon about 0.30 to about 0.65%

manganese about 0.30 to about 2.5%

at least one element from the group consisting of aluminum, niobium, titanium and vanadium, and mixtures thereof, in an effective amount for grain refining up to about 0.35%

iron balance; and

cold forming said blank by upsetting, forging or extrusion, at ambient temperature to provide a part having a desired geometric configuration, whereby the mechanical properties of tensile strength and yield strength of said part are substantially the same or greater than said blank.

10. The method of claim 9 wherein said blank of high-strength steel has a tensile strength of at least about 150,000 psi and a yield strength of at least about 130,000 psi.

11. The method of claim 9 wherein said blank of high-strength steel material has a microstructure of fine pearlite in a ferritic matrix.

-14-

12. The method of claim 1, said part being selected from the group of parts consisting of various types of bolts, screws, axles, and cam shafts.

5 13. The method of claim 9, said part being selected from the group of parts consisting of various types of bolts, screws, axles, and cam shafts.

INTERNATIONAL SEARCH REPORT

International Application No.

P US 93/12043

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 5 C21D7/10 C22C38/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C21D C22C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB,A,1 535 775 (VEB SCHRAUBENKOMBINAT) 13 December 1978 see the whole document ---	1,9
A	US,A,5 094 698 (H.M.GALLAGHER JR) 10 March 1992 cited in the application ---	
A	US,A,4 289 548 (J.H.BUCHER ET AL) 15 September 1981 ---	
A	US,A,3 904 445 (H.M.GALLAGHER JR) 9 September 1975 cited in the application ---	
A	US,A,3 001 897 (E.S.NACHTMAN) 26 September 1961 ---	
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

13 April 1994

Date of mailing of the international search report

25. 04. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax (+31-70) 340-3016

Authorized officer

Mollet, G

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/US 93/12043

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE,A,34 34 743 (M.A.N.-B & W DIESEL GMBH) 3 April 1986 ---	
P,X	WO,A,93 18189 (CONSOLIDATED METAL PRODUCTS) 16 September 1993 cited in the application see claims -----	1-7

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

US 93/12043

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-1535775	13-12-78	NONE	
US-A-5094698	10-03-92	AU-A- 8300891	26-05-92
		CA-A- 2093905	25-04-92
		EP-A- 0554257	11-08-93
		JP-T- 6501743	24-02-94
		WO-A- 9207966	14-05-92
		US-A- 5236520	17-08-93
US-A-4289548	15-09-81	NONE	
US-A-3904445	09-09-75	NONE	
US-A-3001897		NONE	
DE-A-3434743	03-04-86	NONE	
WO-A-9318189	16-09-93	US-A- 5236520	17-08-93